

## Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., August 27, 1888.

Assayer's Report of Test Coins, issued at the Mint of the U. S.  
at Philadelphia, in May, 1888.

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.			
		GRAINS.	DEC.	GOLD.		SILVER.	
Double Eagle.....	100	411	20		0	899	8
Eagle.....		412	98		"	900	4
Half Eagle.....	101	413	12		"	899	8
Three Dollars.....		412	99		"	900	9
Quarter Eagle.....	103	411	60		"	900	0
One Dollar.....		412	05-		"	900	4
Standard Dollar...	105	413	20		"	900	4
		412	55-		"	900	4
Half Dollar.....	107	412	60		"	900	9
Quarter Dollar....		412	90		"	900	2
Dime.....	109	412	40		"	900	0
		412	23		"	900	2
	112	412	55-		0	900	2
		413	40		"	900	7

W. R. Lawson  
Assayer.

## Treasury Department,

(2)

BUREAU OF THE MINT,

Washington, D. C., August 27, 1888.

Assayer's Report of Test Coins, issued at the Mint of the U. S.  
at Philadelphia, in May, 1888.

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.			
		GRAINS.	DEC.	GOLD.		SILVER.	
Double Eagle.....	113	412	49		0	900	97
		412	85		"	899	85
Eagle.....	114	412	80		"	899	85
		412	89		"	900	45
Half Eagle.....	116	412	40		"	899	35
		412	19		"	900	45
Three Dollars.....	119	412	04		"	900	75
		412	30		"	898	65
Quarter Eagle.....	121	412	30		"	899	15
		411	70		"	899	15
One Dollar.....	123	412	65		"	899	1
		412	55		"	900	2
Standard Dollar...							
Half Dollar.....							
Quarter Dollar...							
Dime.....							
Average Weight		412	497	Av. Fineness		900	065

W. P. Lauren  
Assayer.

# Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., *August 27, 1888.*

Assayer's Report of Test Coins, issued at the Mint of the U. S.  
at *Philadelphia*, in *May*, 1888:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle.....	1111	38	70		
Eagle.....		38	43		
Half-Eagle.....		38	30		
Three Dollars.....		38	04		
Quarter Eagle.....		38	50		
One Dollar.....		38	68		
Standard Dollar...		38	45-		
Half-Dollar.....		38	55-		
Quarter Dollar....		38	40		
Dime.....		38	53		
Average Weight		38	458		

0 899 3

*W. P. Lawrence*

Assayer.



## Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., August 26, 1888.

Assayer's Report of Test Coins, issued at the Mint of the U. S.  
at Philadelphia, in May, 1888:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.	
		GRAINS.	DEC.	GOLD.	SILVER.
Double Eagle.....	117	38	08		
Eagle.....		38	58		
Half-Eagle.....		38	23		
Three Dollars.....		38	06		
Quarter-Eagle.....		38	93		
One Dollar.....		38	73	0	899 6
Standard Dollar...		38	38		
Half Dollar.....		38	83		
Quarter-Dollar....		38	09		
Dime.....		38	63		
Average Weight		38	454		

W. P. Lawren

Assayer.

## Treasury Department,

BUREAU OF THE MINT,

Washington, D. C., August 27, 1888.

Assayer's Report of Test Coins, issued at the Mint of the U. S.  
at Philadelphia, in May, 1888:

DENOMINATION.	No. of Delivery.	WEIGHT.		FINENESS.			
		GRAINS.	DEC.	GOLD.		SILVER.	
Double Eagle.....	18	515	90	900	0	7	
E. Eagle.....	19	515	71	900	1	7	
<i>Assay Eagle</i> .....		515	805	900	05		<i>Ar. Fineness</i>
Three Dollars.....							
<del>Quarter Eagle</del> .....	16	257	90	900	0	8	
One Dollar.....							
Standard Dollar...							
Half Dollar.....							
Quarter Dollar....							
Dime.....							

W. A. Lauren

Assayer.

[Table One:]

1

Treasury Department,  
Bureau of the Mint,  
Washington, D.C.,  
August 27, 1888

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in May, 1888:

Denomination.	No. of Delivery	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Standard Silver Dollar.	100	411	20		0	899.8
		412	98		"	900.4
	101	413	12		"	899.8
		412	99		"	900.9
	103	411	60		"	900.0
		412	05		Tr.	900.4
	105	413	20		"	900.4
		412	55		"	900.4
	107	412	60		"	900.9
		412	90		"	900.2
	109	412	40		"	900.0
		412	23		"	900.2
	112	412	55		0	900.2
		413	40		"	900.7

W.P. Lauren  
Assayer.

[Table Two:]

2

Treasury Department,  
Bureau of the Mint,  
Washington, D.C.,  
August 27, 1888

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in May, 1888:

Denomination.	No. of Delivery	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Standard Silver Dollars	113	412	49		0	900.9
		412	85		"	899.8
	114	412	80		"	899.8
		412	89		"	900.4
	116	412	40		"	899.3
		412	19		"	900.4
	119	412	04		"	900.7
		412	30		"	898.6
	121	412	30		"	899.1
		411	70		"	899.1
	123	412	65		"	899.1
		412	55		Tr.	900.2
Average Weight		412	497	Av. Fineness		900.065

W.P. Lauren  
Assayer.

[Table Three:]

3

Treasury Department,  
Bureau of the Mint,  
Washington, D.C.,  
August 27, 1888

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in May, 1888:

Denomination.	No. of Delivery	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	111	38	70			
		38	43			
		38	30			
		38	04			
		38	50			
		38	68		0	899.3
		38	45			
		38	55			
		38	40			
		38	53			
Average Weight		38	458			

W.P. Lauren  
Assayer.



[Table Four:]

4

Treasury Department,  
Bureau of the Mint,  
Washington, D.C.,  
August 26, 1888

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in May, 1888:

Denomination.	No. of Delivery	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Dimes	117	38	08			
		38	58			
		38	23			
		38	06			
		38	93			
		38	73		0	899.6
		38	38			
		38	83			
		38	09			
		38	63			
Average Weight		38	454			

W.P. Lauren  
Assayer.

[Table Five:]

5

Treasury Department,  
Bureau of the Mint,  
Washington, D.C.,  
August 27, 1888

Assayer's Report of Test Coins, issued at the Mint of the U.S. at Philadelphia, in May, 1888:

Denomination.	No. of Delivery	Weight. Grains.	Weight. Dec.	Fineness. Gold.		Fineness. Silver.
Double Eagle	18	515	90	900	0	7
D. Eagle	19	515	71	900	1	7
Average Weight		515	805	900	05	Av. Fineness
Eagle	16	257	90	900	0	8

W.P. Lauren  
Assayer.